

February 20, 2017

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.


Work Order No.: 242946 Lot No.: 325625 Date: 11/17/16

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-1587	5/8" EHS G.S.*	42,400	43,800	103.3	Strand broke mid span. No slip from either dead-end.
			37,720	89.0	Strand broke mid span. No slip from either dead-end.**
			43,830	103.4	Strand broke mid span. No slip from either dead-end.
		AVERAGE	41,783	98.57	

*Strand is from National Strand

**After the low result for the second sample, a third sample was tested.

Regards,



Scott L. Sanderson
Senior Quality Engineer

RMB
cc: File 94
J. Reilly