

August 29, 2017

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 600602 Lot No.: 600602 Date: 7/25/17

110211 020102 1101 000002 200 1101 000002 20100 1720721					
BRACE-GRIP®	Strand	Strand	Maximum	% of	Failure Mode at
Dead-End	Size	RBS	Load	RBS	Maximum Load
CAT. NO.	(in.)	(lbs.)	(lbs.)		
					Strand Broke mid
			53,470	126.1	span. No slip from
	5/8"				either dead-end.
BRG-1587	EHS	42,400			Strand Broke mid
	G.S.*		53,680	126.6	span. No slip from
					either dead-end.
		AVERAGE	53,575	126.3	

^{* =} Strand is from WireCo.

Regards,

Scott L. Sanderson Senior Quality Engineer

RMB

cc: File 94
J. Reilly