

March 27, 2014


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 108390      Lot No.: 108390      Date: 1/31/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2583	3/8" EHS G.S.	15,400	17,948	116.5	Strand broke 2' from DE on tailstock side.
			17,943	116.5	Strand broke 1' from DE on tailstock side.
AVERAGE			17,946	116.5	

Regards,



**Scott L. Sanderson**  
Corporate Quality Assurance Engineer

ma

cc: File 94  
J. Reilly