

October 24, 2016


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 241933 Lot No.: 241933 Date: 10/18/16

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2583	3/8" EHS G.S.	15,400	17,340	112.6	Strand broke mid span. No slip from either dead-end.
			17,253	112.0	Strand broke mid span. No slip from either dead-end.
		AVERAGE	17,297	112.3	

Regards,



Scott L. Sanderson
Senior Quality Engineer

RMB
cc: File 94
J. Reilly