

November 22, 2017


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 302787    Lot No.: 302787    Date: 11/15/17

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2583	3/8" EHS G.S.	15,400	16,956	110.1	Strand broke mid span. No slip from either dead-end.
			16,973	110.2	Strand broke mid span. No slip from either dead-end.
		AVERAGE	16,965	110.2	

Regards,



Scott L. Sanderson  
Senior Quality Engineer

RMB  
cc: File 94  
J. Reilly