

September 9, 2019

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Lot No.: 8353

Date: 7/26/19

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2583	3/8" EHS G.S.	15,400	17,321	112.5	Strand broke mid span. No slip from either dead-end.
			17,397	113.0	Strand broke mid span. No slip from either dead-end.
		AVERAGE	17,359	112.7	

Regards,



Scott L. Sanderson  
Senior Quality Engineer

RMB  
cc: File 94  
M. Miller