

October 3, 2019

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Lot No.: 9253

Date: 9/30/19

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2583	3/8" EHS G.S.	15,400	17,357	112.7	Strand broke mid span. No slip from either dead-end.
			17,335	112.6	Strand broke mid span. No slip from either dead-end.
		AVERAGE	17,346	112.6	

Regards,



Scott L. Sanderson
Senior Quality Engineer

RMB
cc: File 94
M. Miller