

January 31, 2020

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.


Lot No.: 426444

Date: 1/10/20

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2585	1/2" EHS G.S.	26,900	26,943	100	Strand broke mid span. No slip from either dead-end.
			31,600	117	Strand broke mid span. No slip from either dead-end.
			31,607	117	Strand broke mid span. No slip from either dead-end.
		AVERAGE	30,050	112	

Note - Sample 2 and 3 were tested with a different batch of strand after the low result from sample 1.

Regards,



Scott L. Sanderson
Senior Quality Engineer

RMB
cc: File 94
M. Miller