

March 27, 2014


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 97586      Lot No.: 97586      Date: 11/1/13

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND RBS (lbs.)	MAXIMUM LOAD (lbs.)	% RBS	FAILURE MODE AT MAX. LOAD
BRG-2585	1/2" EHS G.S.	26,900	30,176	112.2	Strand failed 1' from ram.
			30,151	112.1	Strand failed 1 1/2' from ram.
AVERAGE			30,164	112.2	

Regards,



Scott L. Sanderson  
Corporate Quality Assurance Engineer

ma

cc: File 94  
J. Reilly