

December 20, 2018

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 363470 Lot No.: 363470 Date: 12/10/18

WOIN Older No.: 303170 Hot No.: 303170 Bate: 12/10/10					
BRACE-GRIP®	Strand	Strand	Maximum	% of	Failure Mode at
Dead-End	Size	RBS	Load	RBS	Maximum Load
CAT. NO.	(in.)	(lbs.)	(lbs.)		
BRG-2585US	1/2" EHS G.S.	26,900	34,358	127.7	Strand broke mid span. No slip from either dead-end.
			34,298	127.5	Strand broke mid span. No slip from either dead-end.
		AVERAGE	34,328	127.6	

Regards,

Scott L. Sanderson Senior Quality Engineer

RMB

cc: File 94 M. Miller