

March 27, 2014

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 111422      Lot No.: 111422      Date: 2/28/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND RBS (lbs.)	MAXIMUM LOAD (lbs.)	% RBS	FAILURE MODE AT MAX. LOAD
BRG-2585	1/2" EHS G.S.	26,900	29,974	111.4	Strand failed midspan.
			30,048	111.7	Strand failed midspan.
AVERAGE			30,011	111.6	

Regards,



Scott L. Sanderson  
Corporate Quality Assurance Engineer

ma

cc: File 94  
J. Reilly