

March 27, 2014


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 114834 Lot No.: 114834 Date: 3/7/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND RBS (lbs.)	MAXIMUM LOAD (lbs.)	% RBS	FAILURE MODE AT MAX. LOAD
BRG-2585	1/2" EHS G.S.	26,900	29,953	111.3	Strand failed midspan, no slip.
			30,005	111.5	Strand failed midspan, no slip.
AVERAGE			29,979	111.4	

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly