

October 5, 2017


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 293388 Lot No.: 293388 Date: 9/19/17

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2585US	1/2" EHS G.S.	26,900	30,824	114.6	Strand broke mid span. No slip from either dead-end.
			30,756	114.3	Strand broke mid span. No slip from either dead-end.
		AVERAGE	30,790	114.4	

Regards,



Scott L. Sanderson
Senior Quality Engineer

RMB
cc: File 94
J. Reilly