

February 24, 2015


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 217973      Lot No.: 217973      Date: 1/27/15

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-1587	5/8" EHS G.S.	41,400	47,103	111.1	Strand failed near tailstock at max load; no slip
			47,077	111.1	Strand failed near tailstock at max load; no slip
AVERAGE			47,090	111.1	

Regards,



**Scott L. Sanderson**  
Corporate Quality Assurance Engineer

ma

cc: File 94  
J. Reilly