

November 3, 2014


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 079412 Lot No.: 079412 Date: 9/18/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-1587	5/8" EHS G.S.	41,400	46,977	113.5	Strand broke near end of ram DE; no slip.
			46,831	113.1	Four wires of strand failed midspan; no slip.
AVERAGE			46,904	113.3	

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly