

April 29, 2015


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 164171      Lot No.: 164171      Date: 4/10/15

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2580	1/4" EHS G.S.	6,650	7,446	112.0	Strand failed tailstock side of DE; no slip.
			7,441	111.9	Strand failed ram side of DE; no slip.
AVERAGE			7,444	112.0	

Regards,



**Scott L. Sanderson**  
Corporate Quality Assurance Engineer

ma

cc: File 94  
J. Reilly