

November 3, 2014


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 137036 Lot No.: 137036 Date: 8/27/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2580	1/4" EHS G.S.	6,650	7,449	112.0	Strand failed midspan; no slip. NOTE: Sample was loaded at 3,325 lbf/sec in error.
			7,327	110.2	Strand failed midspan; no slip.
AVERAGE			7,388	111.1	

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly