

December 15, 2015


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 185879 Lot No.: 185879 Date: 10/27/15

| BRACE-GRIP® DE CAT NO. | STRAND SIZE (in.) | STRAND RBS (lbs.) | MAXIMUM LOAD (lbs.) | % RBS | FAILURE MODE AT MAX. LOAD |
|---------------------------|----------------------|-------------------------|---------------------------|----------|------------------------------------|
| BRG-2583 | 3/8" EHS G.S. | 15,400 | 17,238 | 111.9 | Strand broke ram side; no slip. |
| | | | 17,099 | 111.0 | Strand broke ram side; no slip. |
| | | | | | |
| AVERAGE | | | 17,169 | 111.5 | |

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly