

July 30, 2013


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 127528 Lot No.: 127528 Date: 6/19/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2583	3/8" EHS G.S.	15,400	17,874f	116.1	Strand broke midspan; no slip.
			17,971	116.7	Strand broke midspan; no slip.
AVERAGE			17,922.5	116.4	

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly