

November 3, 2014


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 136879      Lot No.: 136879      Date: 8/28/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2583	3/8" EHS G.S.	15,400	17,779	115.4	Strand failed midspan; no slip.
			17,935	116.5	Strand failed midspan; no slip.
AVERAGE			17,857	116.0	

Regards,



**Scott L. Sanderson**  
Corporate Quality Assurance Engineer

ma

cc: File 94  
J. Reilly