

February 24, 2015


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 151553      Lot No.: 151553      Date: 1/12/15

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND RBS (lbs.)	MAXIMUM LOAD (lbs.)	% RBS	FAILURE MODE AT MAX. LOAD
BRG-2585	1/2" EHS G.S.	26,900	30,997	115.2	Strand failed near tailstock at max load; no slip
			31,300	116.4	Strand failed near tailstock at max load; no slip
AVERAGE			31,149	115.8	

Regards,



Scott L. Sanderson  
Corporate Quality Assurance Engineer

ma

cc: File 94  
J. Reilly