



PREFORMED LINE PRODUCTS



P.O. BOX 91129 • CLEVELAND, OHIO 44101 • (440) 461-5200

May 30, 2007

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 256592 Lot No.: 256592 Date: 5/25/07

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2586	9/16" EHS GS	30,000	40117	114.6	Strand failed
			40214	114.9	Strand failed
AVERAGE			40165.5	114.8	

Regards,

Scott L. Sanderson
Corporate Quality Assurance Engineer

ma