

March 29, 2016

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

MOTK OTACT MO T/OOTO MOC MO T/OOTO DALC. 0/T/T.	Work	Order	No.:	178618	Lot No.:	178618	Date:	8/19/15	5
---	------	-------	------	--------	----------	--------	-------	---------	---

BRACE-GRIP®	Strand	Strand	Maximum	% of	Failure Mode at
Dead-End	Size	RBS	Load	RBS	Maximum Load
CAT. NO.	(in.)	(lbs.)	(lbs.)		
	1/2"	26,900	31,116	115.7	Strand broke mid span. No slip occurred.
BRG-2585	EHS G.S.		31,132	115.7	Strand broke near one dead-end. No slip occurred.
		AVERAGE	31,124	115.7	

Regards,

Scott Sanderson

Scott L. Sanderson Senior Quality Engineer

