

May 27, 2016


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 210490    Lot No.: 210490    Date: 5/19/16

| BRACE-GRIP®<br>Dead-End<br>CAT. NO. | Strand<br>Size<br>(in.) | Strand<br>RBS<br>(lbs.) | Maximum<br>Load<br>(lbs.) | % of<br>RBS | Failure Mode at<br>Maximum Load                      |
|-------------------------------------|-------------------------|-------------------------|---------------------------|-------------|--|
| BRG-2580                            | 1/4"<br>EHS<br>G.S.     | 6,650                   | 7,933                     | 119.3       | Strand broke mid span. No slip from either dead-end. |
|                                     |                         |                         | 7,935                     | 119.3       | Strand broke mid span. No slip from either dead-end. |
|                                     |                         | AVERAGE                 | 7,934                     | 119.3       |  |

Regards,



Scott L. Sanderson  
Senior Quality Engineer

RMB  
cc: File 94  
J. Reilly