

January 8, 2015


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 150636 Lot No.: 150636 Date: 12/2/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2582	5/16" EHS G.S.	11,200	12,108	108.1	Strand broke at max. load; no slip
			12,176	108.7	Strand broke at max. load; no slip
AVERAGE			12,142	108.4	

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly