

January 17, 2018

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 307833 Lot No.: 307833 Date:	: 1/8/18
--	----------

BRACE-GRIP®	Strand	Strand	Maximum	% of	Failure Mode at
Dead-End	Size	RBS	Load	RBS	Maximum Load
CAT. NO.	(in.)	(lbs.)	(lbs.)		
BRG-2580	1/4" EHS G.S.	6,650	8,205	123.4	Strand broke mid span. No slip from either dead-end.
			8,158	122.7	Strand broke mid span. No slip from either dead-end.
		AVERAGE	8,182	123.0	

Regards,

Scott Sanderson

Scott L. Sanderson Senior Quality Engineer

RMB cc: File 94 M. Miller