

September 12, 2016

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 235236 Lot No.: 235236 Date: 9/9/16

WOIR Older No.: 255250 Hot No.: 255250 Date: 5/5/10					
BRACE-GRIP®	Strand	Strand	Maximum	% of	Failure Mode at
Dead-End	Size	RBS	Load	RBS	Maximum Load
CAT. NO.	(in.)	(lbs.)	(lbs.)		
	1/4"		7,904	118.9	Strand broke mid span. No slip from either dead-end.
BRG-2580	EHS G.S.	6,650	7,957	119.7	Strand broke mid span. No slip from either dead-end.
		AVERAGE	7,931	119.3	

Regards,

Scott L. Sanderson Senior Quality Engineer

RMB

cc: File 94
J. Reilly