

January 8, 2015


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 149832      Lot No.: 149832      Date: 12/1/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2583	3/8" EHS G.S.	15,400	18,030	117.1	Strand broke midspan; no slip
			18,036	117.1	Strand broke midspan; no slip
AVERAGE			18,033	117.1	

Regards,



**Scott L. Sanderson**  
Corporate Quality Assurance Engineer

ma

cc: File 94  
J. Reilly