

December 15, 2015


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 185247 Lot No.: 185247 Date: 10/14/15

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND RBS (lbs.)	MAXIMUM LOAD (lbs.)	% RBS	FAILURE MODE AT MAX. LOAD
BRG-2585	1/2" EHS G.S.	26,900	30,782	114.4	All but two strands broke midspan; no slip
			30,846	114.7	Strand broke midspan.
AVERAGE			30,814	114.6	

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly