

November 3, 2014

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 135886      Lot No.: 135886      Date: 9/9/14

| BRACE-GRIP® DE<br>CAT NO. | STRAND<br>SIZE (in.) | STRAND<br>RBS<br>(lbs.) | MAXIMUM<br>LOAD<br>(lbs.) | %<br>RBS | FAILURE MODE AT<br>MAX. LOAD          |
|---------------------------|----------------------|-------------------------|---------------------------|----------|---------------------------------------|
| BRG-2585                  | 1/2" EHS<br>G.S.     | 26,900                  | 30,643                    | 113.9    | Strand failed<br>midspan; no<br>slip. |
|                           |                      |                         | 30,720                    | 114.2    | Strand failed<br>midspan; no<br>slip. |
|                           |                      |                         |                           |          |                                       |
| AVERAGE                   |                      |                         | 30,682                    | 114.1    |                                       |

Regards,



Scott L. Sanderson  
Corporate Quality Assurance Engineer

ma

cc: File 94  
J. Reilly