



November 8, 2022

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Lot No.: 577558

Date: 11/1/22

| BRACE-GRIP®<br>Dead-End CAT.<br>NO. | Strand<br>Size (in.) | Strand<br>RBS (lbs.) | Maximum<br>Load (lbs.) | % of<br>RBS | Failure Mode at Maximum<br>Load                             |
|-------------------------------------|----------------------|----------------------|------------------------|-------------|---|
| BRG-2582                            | 5/16"<br>EHS<br>G.S. | 11,200               | 13,191                 | 118         | Strand broke mid span.<br>No slip from either dead-<br>end. |
|                                     |                      |                      | 13,193                 | 118         | Strand broke mid span.<br>No slip from either dead-<br>end. |
|                                     | AVERAGE              | 13,192               | 118                    |             |   |

Regards,

Scott L. Sanderson

Senior Quality Engineer

RMB

cc: File 94, M. Miller

PLP.COM