

June 5, 2019

Testing was performed in accordance with:


ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 387475 Lot No.: 316464 Date: 5/17/19

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-1587	5/8" EHS G.S.*	42,400	54,300	128.1	Test stopped at max load. No strand failure or slip from either dead-end.
			55,100	130.0	Test stopped at max load. No strand failure or slip from either dead-end.
		AVERAGE	54,700	129.0	

* = Strand is from National Strand.

Regards,



Scott L. Sanderson
Senior Quality Engineer

RMB
cc: File 94
M. Miller