



**PREFORMED** LINE PRODUCTS

March 27, 2014

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 105093      Lot No.: 105093      Date: 1/2/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2580	1/4" EHS G.S.	6,650	7,372	110.9	Strand failed 2" from DE on tailstock side
			7,336	110.3	Strand failed 1' from DE on tailstock side
AVERAGE			7,354	110.6	

Regards,

**Scott L. Sanderson**  
Corporate Quality Assurance Engineer

ma

cc: File 94  
J. Reilly

