



PREFORMED LINE PRODUCTS

March 27, 2014

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 109733 Lot No.: 109733 Date: 1/29/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2580	1/4" EHS G.S.	6,650	7,389	111.1	Strand failed 2' from DE on tailstock side
			7,419	111.6	Strand failed 1' from DE on tailstock side
AVERAGE			7,404	111.4	

Regards,

Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly

