

November 18, 2019

Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.


Lot No.: 9290

Date: 10/31/19

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2582	5/16" EHS G.S.	11,200	11,230	100	One dead-end slipped at max load. No strand failure occurred.**
			13,182	117	One dead-end slipped at max load. No strand failure occurred.
			13,109	117	Strand broke mid span. No slip from either dead-end.
			13,154	117	Strand broke mid span. No slip from either dead-end.
			13,080	117	Strand broke mid span. No slip from either dead-end.
			AVERAGE	12,736	114

** = After sample slipped at 100% RBS, 3 additional samples were tested.

Regards,



Scott L. Sanderson
Senior Quality Engineer

RMB
cc: File 94
M. Miller