

September 5, 2018


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 343876 Lot No.: 343876 Date: 8/16/18

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2582	5/16" EHS G.S.	11,200	13,433	119.9	Strand broke mid span. No slip from either dead-end.
			13,481	120.4	Strand broke mid span. No slip from either dead-end.
		AVERAGE	13,457	120.2	

Regards,



Scott L. Sanderson
Senior Quality Engineer

RMB
cc: File 94
M. Miller