

March 27, 2014


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 106588 Lot No.: 106588 Date: 1/10/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND RBS (lbs.)	MAXIMUM LOAD (lbs.)	% RBS	FAILURE MODE AT MAX. LOAD
BRG-2585	1/2" EHS G.S.	26,900	30,134	112.0	Strand failed 1' from DE on tailstock side.
			30,099	111.9	Strand failed at end of DE on tailstock side.
AVERAGE			30,117	112.0	

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly