

April 14, 2016


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fitting to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 206533 Lot No.: 206533 Date: 3/21/16

BRACE-GRIP® Dead-End CAT. NO.	Strand Size (in.)	Strand RBS (lbs.)	Maximum Load (lbs.)	% of RBS	Failure Mode at Maximum Load
BRG-2585	1/2" EHS G.S.	26,900	30,702	114.1	Strand broke mid span. No slip occurred.
			30,992	115.2	Strand broke near one dead-end. No slip occurred.
		AVERAGE	30,847	114.7	

Regards,



Scott L. Sanderson
Senior Quality Engineer

RMB
cc: File 94
J. Reilly