

May 11, 2015


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 307528 Lot No.: 307528 Date: 2/26/15

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-1587	5/8" EHS G.S.	41,400	43,830	103.4	Strand broke at max. load. No slip.
			44,480	104.9	Strand broke at max. load. Slight slip.
			44,155	104.2	
AVERAGE					

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly