

April 17, 2014


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 113815 Lot No.: 113815 Date: 3/28/14

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2583	3/8" EHS G.S.	15,400	18,215	118.3	Strand broke midspan.
			18,251	118.5	Strand broke midspan.
AVERAGE			18,233	118.4	

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly