

May 28, 2015


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 164630 Lot No.: 164630 Date: 4/23/15

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2583	3/8" EHS G.S.	15,400	18,054	117.2	Strand broke at max. load; no slip.
			18,190	118.1	Strand broke at max. load; no slip.
AVERAGE			18,122	117.7	

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly