

May 29, 2015


Testing was performed in accordance with:

ASCE 19-96, 3.2.2., which requires fittings to develop an ultimate strength of at least 110% of the specified nominal cable strength.

Work Order No.: 166764 Lot No.: 166764 Date: 5/11/15

BRACE-GRIP® DE CAT NO.	STRAND SIZE (in.)	STRAND MBS (lbs.)	MAXIMUM LOAD (lbs.)	% MBS	FAILURE MODE AT MAX. LOAD
BRG-2583	3/8" EHS G.S.	15,400	18,110	117.6	Strand failed 3" from tailstock DE.
			15,642	101.6	Strand failed mid span; one wire failed at ram end.
AVERAGE			16,876	109.8	

Regards,



Scott L. Sanderson
Corporate Quality Assurance Engineer

ma

cc: File 94
J. Reilly